

Data Sheet **Compri-pvc-L**

<u>density</u>	ca. 120 +/-20 kg/m ³	
<u>temperature range</u>	-20°C to +80°C	
<u>elongation at break</u>	ca. 137%	DIN 53571
<u>compressive strength</u> at 40 % deformation	109,7 N/cm ²	DIN 53576/B
<u>tensile strength</u>	0,24 N/mm ²	DIN 53571
<u>residual deformation after compression</u> crushing of 50%, for 72h	8% after 30 min	DIN 53572
<u>adhesive</u>	acrylic, with net	
<u>fire resistance</u>	self extinguishing	CLASS 1
<u>release liner</u>	silicone paper (brown)	
<u>resistance to high humidity</u>	good	
<u>ageing resistance</u>	very good	
<u>tolerance</u>		DIN 7715 rough

This information only relate to the rubber foam material and not to the adhesive or the adhesive property.
All mentioned data are guideline values, a commitment cannot be deducted.